



Scotch-Weld™ DP490

Product Data Sheet

Date: March 2020
Supersedes: February 2020

Product Description

Scotch-Weld™ DP490 is a black, thixotropic, gap filling two components epoxy adhesive with particularly good application characteristics. It is designed for use where toughness and high strength are required.

Key Features

- Cures at room temperature; cure rate may be accelerated by the application of mild heat.
- Convenient 2:1 mix ratio by volume
- Mixed adhesive is low flow for ease of application
- Toughened epoxy system with good elevated temperature resistance
- Suitable for Composite assemblies

Typical Uncured Properties

	Base	Accelerator
Base	Toughened epoxy	Modified amine
Colour	Black	Off-White
Mix Ratio - by volume - by weight	100 100	50 50

	Test Method	Units	Base	Accelerator
Specific Gravity	ISO 2811.1	g/cm ³	1.04	1.02
Viscosity	ISO 2555	mPas	313 000	78 000
Work Life ⁽¹⁾	-	min	approx. 163	

(1) Maximum time allowed after applying adhesive to one substrate before bond must be closed and fixed in place.

Performance Characteristics

	Test Method	Units	Results
Overlap Shear Strengths -55 °C 23 °C 80 °C	ISO 4587	MPa	22.5 CF 30.8 CF 13.3 CF
Peel Strength ⁽²⁾	EN 2243-2	N/25 mm	170.9 CF
Slump Resistance ⁽³⁾	-	mm	0.5

(2) Floating roller peel values measured using EN 2243-2; adhesives allowed to cure for 24 hours at 23 ± 2 °C and 30 min at 80 ± 3 °C; 25 mm wide samples; 150-200 µm bond line thickness; samples pulled at 150 mm/min; aluminium surfaces etched; substrates used were 1.6 mm thick and 0.5 mm thick aluminium.

(3) A bead of 1/16" thickness and 25.4 mm width applied on an aluminium substrate which is then placed vertically. The slump resistance is measured by the increase of the bead width

Failure modes:

AF: adhesive failure

CF: cohesive failure

SF: substrate failure

Directions for use

For high strength structural bonds, paint, oils, dust, mould release agents and other surface contaminants must be completely removed. However, the amount of surface preparation directly depends on the required bond strength and the environmental ageing resistance desired by user. For specific surface preparations on common substrates, see following information.

Use glove to minimise skin contact. Do not use solvents for cleaning hands

Mixing

For Duo Pack Cartridges

DP 490 is supplied in a dual syringe plastic Duo-Pak cartridge as part of the EPX™ Applicator System. To use, simply insert the Duo-Pak cartridge into the EPX applicator and start plunging the cylinders using light pressure on the trigger. Next, remove the Duo-Pak cartridge cap and expel a small amount of adhesive to be sure both sides of the Duo-Pak cartridge are flowing evenly and freely. If automatic mixing of Part A and Part B is desired, attach the EPX mixing nozzle to the Duo-Pak cartridge and begin dispensing the adhesive. For hand mixing, expel the desired amount of adhesive and mix thoroughly. Mix approximately 15 seconds after uniform colour is obtained.

Surface Preparation:

For high strength structural bonds, paint, oils, dust, mould release agents and other surface contaminants must be completely removed. However, the amount of surface preparation directly depends on the required bond strength and the environmental ageing resistance desired by user.

The following cleaning methods are suggested for common surfaces:

Steel

1. Wipe free of dust with oil-free solvent such as acetone, isopropyl or alcohol solvents*
2. Sandblast or abrade using clean fine grit abrasive.
3. Wipe again with solvent to remove loose particles

Aluminium

1. Alkaline Degrease: Oakite 164 water solution (10 %) at 85 ± 5 °C for 10-20 minutes. Rinse immediately in large quantities of cold running water.
2. Acid Etch: place panels in the following solution for 10 minutes at 65 ± 3 °C
 - Sodium Dichromate 44.8g
 - Sulphuric Acid, 66°Be 332g
 - 2024-T3 aluminium (dissolved 1.5g)
 - Tap water adjust to 1 litre
3. Rinse: rinse panels in clean running tap water.
4. Dry: air dry 15 minutes; force dry 10 minutes at 65 ± 5 °C
5. If primer is to be used, it should be applied within 4 hours after surface preparation.

Plastic/Rubber

1. Wipe with Isopropyl alcohol*
2. Abrade using fine grit abrasives.
3. Wipe with Isopropyl alcohol*

Glass

1. Solvent wipe surface using acetone or MEK*
2. Apply a thin coating (2.5 µm or less) of primer such as Scotch-Weld EC-3901 Primer to the glass surfaces to be bonded and allow the primer to dry before bonding.

(Note: When using solvents, extinguish all ignition sources and observe manufacturer's directions and precautions for handling such materials.*

Storage & Shelf Life

Store product at 16 °C - 27 °C and 45 - 65 % Relative Humidity or refrigerate for maximum shelf life. Rotate stock on a "first in-first out" basis.

Product can be stored in the original package up to

- 39 months for cartridges
- 48 months for bulk

from date of production.

Precautionary Information

Refer to product label and Material Safety Data Sheet for health and safety information before using the product.

For information please contact your local 3M Office.

www.3M.com

For Additional Information

To request additional product information or to arrange for sales assistance, call 3M local subsidiary
Address correspondence to: 3M

Important Notice

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

3M and Scotch-Weld are trademarks of the 3M Company.



Adesivi e Nastri per l'Industria

3M Italia s.r.l.

Via N. Bobbio 21 - 20096 Pioltello (MI)

Tel: 02-7035.1 - Fax: 02-7035.2262

3M™ VHB™ Scotch-Weld™ EPX™ sono marchi di 3M Company.